

## Product name : Magnet in housing, diameter 57 mm, with bore for flat head screw, ferrite

## **PERFORMANCE PARAMETERS**

External diameter	57 [mm]
Aperture diameter for head of a screw	23 [mm]
Internal diameter	6,5 [mm]
Height	10,5 [mm]
With mounting hole	pod płaski łeb śruby
Magnet type	Ferrite
Maximal hoisting capacity	30 [kg]
<ul> <li>The pull force given refers to hoisting capacity measured in optil backing plate a sheet made of low-carbon steel, 10 [mm] thick, acting perpendicularly, in room temperature.</li> <li>Notice: the pull force given should be treated as only a compara An actual pull force depends on the following factors: <ul> <li>air gap (a distance) between holding magnet and an bacca very narrow gap, i.e. 0,5 [mm] can result in decrease in</li> <li>material, of which a backing plate is made (the higher capull force)</li> <li>surface of a backing plate (the smoother the surface, the direction of acting of detaching force)</li> <li>thickness of a backing plate (the backing plate cannot be of magnetic flux is not used for closing of a magnetic circe working temperature (in temperature of 80°[C] pull force</li> </ul> </li> </ul>	of smooth surface and with the force tive value. king plate (in some conditions even n pull force by a half) arbon proportion in steel, the smaller bigger pull force) rce is obtained with perpendicular e too thin, because in such case part cuit) e can be lower of up to 20 per cent)
Coating	Zinc (Zn)
Maximum working temperature	110 °[C]
water-resistant	yes
With a central hole for the screw head	yes
Weight	122 [g]

Holding magnets are simple magnetic circuits composited of a magnet and a steel housing. Because of that, in the holding magnets both magnet poles are used (one works directly, and the second saturates the housing, which also act on the attracted element), they are characterized by a relatively high pull force parallel to significantly reducing of the operating range.

In the holding magnet sintered ferrite magnet was used. Max. working temperature for this holding magnet is **110°[C]**.

We generally recommend individual checking of the holding magnet in any specific working

## **TECHNICAL DRAWING**

